Document made available under the Patent Cooperation Treaty (PCT)

International application number: PCT/US05/003388

International filing date: 02 February 2005 (02.02.2005)

Document type: Certified copy of priority document

Document details: Country/Office: US

Number: 60/541,156


Filing date: 02 February 2004 (02.02.2004)

Date of receipt at the International Bureau: 07 March 2005 (07.03.2005)

Remark: Priority document submitted or transmitted to the International Bureau in

compliance with Rule 17.1(a) or (b)





'4'(d) Anil (100) Vancoda (na 12812; preus ben'is; salanti, codias:

UNITED STATES DEPARTMENT OF COMMERCE

United States Patent and Trademark Office

February 25, 2005

THIS IS TO CERTIFY THAT ANNEXED HERETO IS A TRUE COPY FROM THE RECORDS OF THE UNITED STATES PATENT AND TRADEMARK OFFICE OF THOSE PAPERS OF THE BELOW IDENTIFIED PATENT APPLICATION THAT MET THE REQUIREMENTS TO BE GRANTED A FILING DATE.

APPLICATION NUMBER: 60/541,156 FILING DATE: February 02, 2004

RELATED PCT APPLICATION NUMBER: PCT/US05/03388

Certified by

Under Secretary of Commerce for Intellectual Property and Director of the United States Patent and Trademark Office

PROVISIONAL APPLICATION FOR PATENT COVER SHEET

Mail Stop Provisional Patent Application Commissioner for Patents P.O. Box 1450 Alexandria, VA 22313-1450

This is a request for filing a Provisional Application for Patent under 37 C.F.R. § 1.53(c).

Inventor(s) and Residence (city and either state or foreign country):

Timothy Thomson - West Newbury, Massachusetts

For PROCESS FOR CONTROLLING THE DENSITY AND CONFORMATION OF THE HYDROPHILIC LAYER OF A POLYURETHANE COMPOSITE

- 1. \boxtimes 3 sheets of specification
- 2. A check in the amount of \$80.00 is enclosed in payment of the required fee. The Commissioner is hereby authorized to charge and additional fees or credit any overpayment to Deposit Account No. 50-0540.
- 3. Please direct all communications relating to this application to the address of:

Customer No. 31013

- 4. Applicant hereby states pursuant to 37 C.F.R. § 1.27(c)(1) that Applicant is a small entity.
- 5. This invention was not made by an agency of the United States Government or under a contract with an agency of the United States Government.

Dated: February 2, 2004

Respectfully submitted,

Barry Evans, Es

Reg. No. 22,862

KRAMER LEVIN NAFTALIS & FRANKEL LLP

919 Third Avenue

New York, New York 10022

Express Mail No: ET736210861US Date of Deposit: February 2, 2004 Customer No.: 31013 Docket No.: 161485-00500

PROVISIONAL APPLICATION FOR LETTERS PATENT

Inventor:

Timothy Thomson

Title:

PROCESS FOR CONTROLLING THE DENSITY AND CONFORMATION OF THE HYDROPHILIC LAYER OF A

POLYURETHANE COMPOSITE

Barry Evans Registration No. 22,802 Kramer Levin Naftalis & Frankel LLP 919 Third Avenue New York, New York 10022 (212) 715-9100

> Express Mail No.:ET736210861US Date of Deposit: February 2, 2004

Customer No.: 31013 Docket No.: 161485-00500

Background of the Invention

Thomson in US Patent 6,617,014 teaches the composition and process by which a hydrophilic polyurethane can coat a substantially open cell foam. One of the processes taught in that patent is to emulsify an aqueous phase with a hydrophilic prepolymer and then by means of a nip roller, force the emulsion into the matrix of an open cell hydrophobic polyurethane foam. After curing, the process produces a composite having the strength, structure and other aspects of the open cell polyurethane scaffold and the beneficial properties of the hydrophilic polyurethane as a coating. This is beneficial in a number of product areas including bioremediation of waste or otherwise contaminated water. Certain medical devices are also taught.

As is known the temperature at which the hydrophilic polyurethane is cured to some degree controls the density and the cell structure of the resultant coating.

Description of the Invention

It has been found that by controlling the temperature of the process immediately after application of the hydrophilic prepolymer to the scaffold and before cream time, one can control the density and the conformation of the hydrophilic layer. Specifically, if the curing foam composite is caused to enter a chamber to which is supplied live steam, the hydrophilic polyurethane forms into a low density porous surface. If cold air is pumped through the chamber a dense, nearly hydrogel layer is produced.

EXAMPLE 1

An emulsion of 1 part water to which is added 0.05% Pluronic L62 and 1 part Hypol 2002 is produced in a pin mixer and deposited on a 30ppi polyether polyurethane reticulated foam by means of nip rollers. Within 2 seconds of the first contact of the aqueous phase and the prepolymer, the composite is exposed to live steam in such a way as to

2

Express Mail No.:ET736210861US

Date of Deposit: February 2, 2004

Customer No.: 31013 Docket No.: 161485-00500

immediately elevate the temperature of the composite to 100°C. The steam is in contact with the composite for a minimum of 15 seconds during which time it fully cures as evidenced by a lack of tackiness. Upon microscopic examination, it is determined that a porous hydrophilic coating is produced.

EXAMPLE 2

The composite is prepared as in Example 1, except that the foam enters a chamber to which is pumped air at 4°C. The composite is exposed to the cold air for 30 minutes. Since the foam is still tacky, it is understood that the hydrophilic polyurethane is not fully cured. It is allowed to cure at room temperature for an additional 30 minutes before analysis. Upon microscopic examination, it is determined that a nonporous hydrophilic coating is produced.

Express Mail No.:ET736210861US Date of Deposit: February 2, 2004